

Argiles du Bassin Méditerranéen

MONTMORILLONITES • SMECTITES • KAOLINITES

TECHNICAL DATA SHEET

White Kaolinite Clay Version 2023.1.1

Batch # B7823331 INCI Namel : KAOLINITE # CAS 1332-58-7

Formula: Al2 Si2 O5 (OH)4

CHEMICAL ANALYSIS	PERCENTAGES
SiO2	48 to 50
AL2O3	35 to 37
Fe2O3	0.6 to 0.8
MgO	0.2 to 0.4
K2O	1.9 to 2.3
Na2O	0.1 to 0.2
TiO2	0.04 to 0.06
CaO	0.09 to 0.11

HEAVY METALS	MG/KG
ARSENIC	< 1.7
LEAD	< 66.4
CADMIUM	< 0.01
MERCURY	< 0.01
BACTERIOLOGICAL ANALYSIS	QUANTITY PER G
Aerobies Mésophyll	>15000
Staphylococcus aureus	Absence
Pseudomonas aeruginos	a Absence
Candida Albicans	Absence
Escherichia coli	Absence

Type of clay: Natural Silicate of aluminium and both, Iron and Magnesium

Major Constituent : Kaolinite 100%.

Présentation (dry) : White Clay Powder

Size : This clay come to powder < 40 μ m.

It has to be noted that speaking of a raw mineral chemical analysis is not exactly the same on each part of the quarry without any change of the clay itself.

Clays are mainly characterised by X-ray diffraction and cation exchange capacity.

By this fact we only give an average value for each component.

ADVISORY

Our technicals informations are communicated at best by our knowledge.

They establish simple indications and present results of analyses (microbiology, heavy metals, etc.) which can be incomplete according to the use you have and cannot engage our responsibility, do not exempt you from the necessity of verifying yourself if the delivered products answer the standards, the obligations and the goal needed.

Our advices in materials of safety does not exempt you of determining yourself security measures adapted to the conditions appropriate to your exploitation which we cannot plan, and specially watch the technical qualification and the information of the people called to use, to treat or to be in touch with him.

Argiles du Bassin Méditerranéen

S.A.R.L au capital de 7 622€

N° SIRET : 412 481 970 000 17

N° TVA Intercommunautaire: FR 44412481970

Code APE: 523E

Z.A Le Bas Jasson 985 Chemin du Puits de la Commune 83250 LA LONDE-LES-MAURES - FRANCE Tel : 04.94.66.62.94 | Fax : 04.94.66.67.94

argiles.abm@gmail.com | www.argiles-abm.com